























Product quality		Trendtime 5.50	Trendtime 5.30	Trendtime 6.30
		Vinyl with HDF core board		
Formats		598 x 294 x 5 mm	598 x 292 x 9.6 mm	2200 x 216 x 9.6 mm
Packaging	Pack:	10 Elements / 1.758 m ² / 16.20 Kg	9 Elements / 1.572 m ² / 15.40 Kg	5 Elements / 2.376 m ² / 23.50 Kg
	Pallet:	48 Packs / 84.39 m ² / 792.60 Kg	36 Packs / 56.58 m ² / 569.364 Kg	33 Packs / 78.41 m ² / 790.50 Kg
Tolerances (DIN EN 649)		Tolerances (EN 14085)		
Weight per unit area		≥ 9700 g/m ²	Squareness of the elements (≤ 0.50mm)	
Squareness of the elements (≤ 0.25 mm)		≤ 0.10 mm	Determination of Linearity (≤ 0.30 mm)	
Determination of Linearity (≤ 0.35 mm/m)		≤ 0.20 mm/m	Planeness concave / convex	
			along (≤ 0.50/≤ 1.0 %)	
			wide (≤ 0.10/≤ 0.15 %)	
			Surface flushness	
			(average ≤ 0.15 mm)	
			(max. ≤ 0.20 mm)	
			Opening between installet elements	
			(average ≤ 0.15 mm)	
			(max. ≤ 0.20 mm)	
Guarantee	Domestic area	20 Years (According Parador guarantee conditions)	Notes	<ul style="list-style-type: none"> - Released for glue-down only by PARADOR Application Technology - cleaning an maintenance see instruction - technical changes reserved
	Commercial area	10 Years (According Parador guarantee conditions)		
				
EN 14041:08		PARADOR, 0041 Emissionsgeprüftes Reisprodukt nach DIBt-Grundsätzen ECO-INSTITUT	Qualität Fertigung überwacht Funktionalität www.tuv.com ID 0000039917	

Classification			
		Test method	Valuation
	Utility class 23 domestic areas with intensive use	EN 14085 EN 649	Living room, hall, kitchen, home office
	Utility class 33 commercial areas with intensive use	EN 14085 EN 649	Classrooms, small offices, shops
	Utility class 42 industrial areas with medium use	EN 14085 EN 649	Storage rooms or moderately used Production areas
	Wearlayer	EN 429	0.55 mm
	Abrasion	EN 649	T
	Surface Coating		PUR
	Reaction to fire	EN 13501-1	B _{f1} s1
	Slip resistance	EN 13893 EN 14041	μ ≥ 0,35 DS
	Staining resistance	EN 423	Grad 0, no visible changes
	Light fastness	EN ISO 105 – B02	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	EN 425	Typ W, no visible changes
	Thermal conductivity Underfloor heating – suitable, with the backing material and vapor barrier	EN 12664	Vinyl with HDF core board: 0,068 m ² *K/W Solid vinyl: 0,029 m ² *K/W
	Moving a furniture leg	EN 424	No visible changes
	Indentation-residual	EN 433	≤ 0,10 mm
	Formaldehyde (E1 = 0.1 ppm)		≤ 0,05 ppm
	Accoustical impact noise reduction	ISO 717-2	Vinyl with HDF core board: 15 db Solid vinyl: 13 db (auf Parador Akustic-Protect)
	Dimensional stability	EN 669	Vinyl with HDF core board: along and crosswise ≤0,1 % Solid vinyl: ≤ 0,25 %
	Thickness swelling	ISO 24336 (≤ 18 %)	≤ 16 % (only Solid vinyl:)
	Antimicrobial activity	ISO 22196	Antibacterial
	Slip resistance on an inclined plane	DIN 51130	Surface brushed: R 9 Surface rough sawn: R 10
	REACH		Current requirements are complied
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Changed:	QMB Parador	File:	PA_TDS_Vinyl_Trendtime_EN_12082014
Date:	01.06.2012	Updates at:	www.parador.de
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			12.08.2014