


















Product properties										
Format [mm]	Trendtime 1	Trendtime 3	Trendtime 4	Trendtime 6	Trendtime 8	Trendtime 9				
	2010 x 130 x 13	570 x 95 x 10,5	2010 x 160 x 13	2200 x 185 x 13	1882*x 190 x 15	Basket weave	Strip mix	Mini checkerboard	Old Block pattern	Checkerboard
Top layer:	ca. 3,6 mm	ca. 2,5 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 4 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm
Packaging Pack: m ² /kg	9 Elements 2,352 / 17,1	20 Elements 1,083 / 5,40	9 Elements 2,894 / 19,40	9 Elements 3,663 / 29,304	8 Elements 2,861 / 26,40	8 Elements 3,089 / 23,56	8 Elements 3,256 / 24,832	8 Elements 3,22 / 24,6	8 Elements 3,784 / 28,864	8 Elements 2,827 / 24,6
Pallet: m ² /kg	40 Packs 94,07 / 684,00	36 Packs 38,99 / 194,40	32 Packs 92,621 / 620,64	32 Packs 117,22 / 937,73	32 Packs 91,55 / 844,80	32 Packs 98,842 / 753,92	32 Packs 794,624 / 104,192	32 Packs 103,055 / 787,2	32 Packs 121,088 / 923,648	32 Packs 90,458 / 787,2
Warranty	25 years					Notes				
*	Other formats possible. One short-length per packet possible					- cleaning an maintenance see intruction - technical changes reserved				

Classification Specifications						Tolerances (EN 13489)					
        						Only laquered products:		Admissible difference in length (± 0.1 %)		± 0,05 %	
						Admissible difference in width (± 0.2 mm)		± 0,1 mm			
						Squareness of the element (≤ 0.1 %)		≤ 0,05 %			
						Longitudinal curvature along the element (≤ 0.1 %)		≤ 0,05 %			
						Transverse curvature across the width (≤ 0.1 %)		≤ 0,08 %			
						Height differences of elements (≤ 0.2 mm)		≤ 0,18 mm			
						Moisture content at the time of first delivery (5-9%)		6 – 8 %			

Klassifizierung Produkteigenschaften											
		Testing standard	Valuation								
	Resitance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat								
	Effect of a furniture leg	EN 424	No visible changes								
	Thermal conductivity Underfloor heating – suitable, with the backing material an vapor barrier Formaldehyde (E1 = 0.1 ppm)	EN 12664	<table border="1"> <tr> <td>Trendtime 1 / 4 / 6</td> <td>0,087 m²K/W</td> </tr> <tr> <td>Trendtime 3</td> <td>0,070 m²K/W</td> </tr> <tr> <td>Trendtime 8</td> <td>0,1 m²K/W</td> </tr> <tr> <td>Trendtime 9</td> <td>0,093 m²K/W</td> </tr> </table>	Trendtime 1 / 4 / 6	0,087 m ² K/W	Trendtime 3	0,070 m ² K/W	Trendtime 8	0,1 m ² K/W	Trendtime 9	0,093 m ² K/W
Trendtime 1 / 4 / 6	0,087 m ² K/W										
Trendtime 3	0,070 m ² K/W										
Trendtime 8	0,1 m ² K/W										
Trendtime 9	0,093 m ² K/W										
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0,05 ppm								
	Accoustical impact noise reduction	ISO 717-2	<table border="1"> <tr> <td>Trendtime 1 / 4 / 6 / 8 / 9</td> <td>12 db (with Akustik-Protect 100)</td> </tr> <tr> <td>Trendtime 3</td> <td>14 db (with Akustik-Protect 100)</td> </tr> </table>	Trendtime 1 / 4 / 6 / 8 / 9	12 db (with Akustik-Protect 100)	Trendtime 3	14 db (with Akustik-Protect 100)				
Trendtime 1 / 4 / 6 / 8 / 9	12 db (with Akustik-Protect 100)										
Trendtime 3	14 db (with Akustik-Protect 100)										
	Resitance to roller castor chairs	Privat waste disposal with normal household waste, bulky waste possible									

Classification surface properties					
		Testing standard	Valuation		
			Natural oil	Natural oil (rough sawn)	Lacquer
	Slip resistance	EN 13893	μ ≥ 0,47	μ ≥ 0,47	μ ≥ 0,47
		CEN/TS 15676	46 SRT (SRV wet)	57 SRT (SRV wet)	29 SRT (SRV wet)
			103 SRT (SRV dry)	99 SRT (SRV dry)	51 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _f s1		
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _f s1		
	Chemical resistance	EN 13442	Category 4	Category 4	Category 5
	Bond strength / Cross cut test	ISO 2409	n.n.	n.n.	Category 0
	Slip reststance, inclined plane	DIN 51130	R 10	R 13	R 9

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_EN_2015
Date:	01.05.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 1			Trendtime 3	
Type of wood:	Bamboo	Oak	Lignia	Oak	
Botanical designation / Code (EN 13556):	Phyllostachys pubescens	Quercus petraea Liebl., Quercus robur L. / QCXE	Pinus Radiata	Quercus petraea Liebl., Quercus robur L. / QCXE	
Origin:	CN	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	NZ	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	
Shortcut / sorting / date (internal):	ER-TT1_BAM	ER-TT1-EI	ER-TT1-LIG	ER-TT1-EI	ER-TT1_BAM
	Version 1 2011	Version 5 2011	Version 1 2014	Version 2 2012	Version 1 2011
	N2	N2	N2	A1	N2
Sorting:	Natur	Select	Natur	Natur	Natur
Sound sapwood	-	not permitted	-	not permitted	permitted: up to 25 mm
Knot (intergrown)	-	permitted: up to 15 mm	not permitted	permitted: up to 10 mm	permitted: up to 30 mm
Falling out knot	-	not permitted	not permitted	permitted: up to 3 mm	permitted: up to 10 mm
Pinkknots	-	permitted: Cluster of knots	permitted	permitted	permitted
Filling	permitted	permitted	permitted	permitted	permitted
Slight crack/ haircrack	not permitted	permitted	not permitted	permitted: up to 5 mm	permitted: up to 1x100 mm
Sugar inclusions, mineral inclusions	-	-	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted
Lightning cracks	-	permitted	not permitted	permitted	permitted
Slope of grain	-	permitted	permitted	permitted	permitted
Healthy heart	-	not permitted	-	-	-
Medullary ray	-	permitted	-	-	permitted
Discoloration, colour variation	permitted	permitted: all colours	permitted: slight color variation	permitted: slight color variation	permitted: all colours
White streaks	permitted	permitted	-	not permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_Anhang_EN_2015
Date:	01.03.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015
			Page 1 of 4

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 4				
Type of wood:	Oak	American cherry	American walnut		
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Prunus serotina Ehrh. / PRSR	Juglans nigra L. / JGNG		
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	US	US		
Shortcut / sorting / date (internal):	ES-LH-TT4-EI		ER-TT4-KIR ami.		ER-TT4-SWN
	Version 9 2013		Version 2 2012		Version 4 2013
	N4	N6	N2	N2	N6
Sorting:	Living	Rustikal	Natur	Natur	Living
Sound sapwood	permitted	not permitted	permitted	permitted	permitted
Knot (intergrown)	permitted: up to 40 mm	permitted: up to 80 mm	permitted	permitted: up to 15 mm	permitted
Falling out knot	permitted: up to 25 mm	permitted: up to 40 mm	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 25 mm
Pinkknots	permitted: Cluster of knots	permitted	permitted	permitted	permitted
Filling	permitted	permitted			
Slight crack/ haircrack	permitted	permitted	permitted	permitted	permitted
Sugar inclusions, mineral inclusions	permitted	-	permitted	-	-
Bark pocket	not permitted	permitted	not permitted	not permitted	not permitted
Lightning cracks	permitted: in knots	permitted	not permitted	-	permitted: in knots
Slope of grain	permitted	permitted	permitted	permitted	permitted
Healthy heart	not permitted	permitted	-	-	-
Medullary ray	permitted	permitted	permitted	-	-
Discoloration, colour variation	permitted: slight color variation	permitted: all colours	permitted: all colours	permitted: all colours	permitted: all colours
White streaks	-	-	-	-	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_Anhang_EN_2015		
Date:	01.03.2013	Update:	www.parador.de		
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015	Page 2 of 4	

Free sorting according to EN 13489				
Assortment:	Wide plank			
Characteristics according to EN 1310:	Upper side of the floor board			
Design:	Trendtime 6		Trendtime 8	
Type of wood:	Oak		Oak	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		Quercus mongolica / QCXJ	
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ		CN, RU	
Shortcut / sorting / date (internal):	ER-LH-EI	ER-LH-EI	ER-LH-EI Altholz	ER-TT8-EI
	Version 5 2013	Version 5 2013	Version 4 2014	Version 3 2014
	N3	N4	N7	N8
Sorting:	Natur	Living	Rustikal	Classic
Sound sapwood	not permitted	permitted: up to 30 mm	permitted	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 50 mm	permitted: up to 80 mm	permitted
Falling out knot	permitted: up to 15 mm	permitted: up to 35 mm	permitted: up to 30 mm	permitted: up to 10 mm
Pinknotes	permitted	permitted	permitted	permitted
Filling	permitted	permitted	permitted	permitted
Slight crack/ haircrack	not permitted	permitted: up to 2x200 mm	permitted	permitted
Sugar inclusions, mineral inclusions	permitted	permitted	permitted	-
Bark pocket	not permitted	not permitted	permitted	not permitted
Lightning cracks	permitted: in knots	permitted: in knots	permitted	permitted
Slope of grain	permitted	permitted	permitted	permitted
Healthy heart	not permitted	not permitted	permitted	permitted
Medullary ray	not permitted	not permitted	permitted	permitted
Discoloration, colour variation	permitted: bright colours	permitted: bright colours	permitted: all colours	permitted: all colours
White streaks	-	-	permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	permitted	not permitted
Non-visible parts				
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.				
Comment				
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.				

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_Anhang_EN_2015	
Date:	01.03.2013	Update:	www.parador.de	
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015	Page 3 of 4

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 9				
Type of wood:	Oak				
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE				
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ				
Shortcut / sorting / date (internal):	ER-L-FM-EI	ER-L-M-EI	ER-L-SB-EI	ER-L-HS-EI	ER-LH-WO-EI
	Version 1 2012	Version 1 2012	Version 1 2013	Version 6 2014	Version 3 2012
	Basket weave	Strip mix	Mini checkerboard pattern	Old Block pattern	Checkerboard
Sorting:	Natur	Living	Natur	Living	Living
Sound sapwood	not permitted	not permitted	not permitted	permitted	not permitted
Knot (intergrown)	not permitted	permitted: up to 25 mm	not permitted	permitted: up to 30 mm	permitted: up to 25 mm
Falling out knot	not permitted	permitted: up to 15 mm	not permitted	permitted: up to 10 mm	permitted: up to 10 mm
Pinkknots	permitted: up to 2 mm	permitted: Cluster of knots	permitted: up to 5 mm	permitted	permitted: Cluster of knots
Filling	permitted: up to 5 mm	permitted: up to 15 mm	permitted	permitted: up to 10 mm	permitted: up to 25 mm
Slight crack/ haircrack	not permitted	not permitted	not permitted	permitted	not permitted
Sugar inclusions, mineral inclusions	-	-	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	permitted
Lightning cracks	not permitted	permitted	not permitted	permitted	-
Slope of grain	not permitted: strong flader	permitted	permitted: straight flader	permitted	permitted
Healthy heart	-	permitted	-	permitted	not permitted
Medullary ray	permitted	permitted	permitted	-	permitted
Discoloration, colour variation	permitted: slight color variation	permitted	permitted: slight color variation	permitted	permitted: slight color variation
White streaks	-	permitted	permitted	permitted	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_Anhang_EN_2015		
Date:	01.03.2013	Update:	www.parador.de		
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015	Page 4 of 4	